

Updated Target Values – Smooth Newsprint

Grammage (g/m²)	42.5	45.0	48.8
Caliper (µm)	54	57	62
Density (kg/m ³)	780	790	790
Moisture Content (%)	9.0	9.0	9.0
Filler Content (%)	13	13	13
Parker Print Surf (µm)	3.0	3.0	3.0
Air Permeance (µm/Pas)	3.1	2.7	2.3
Tensile Strength MD (kN/m)	2.7	2.9	3.1
Stretch MD (%)	1.1	1.1	1.2
TEA (J/m ²)	18.0	20.0	23.0
Opacity (%)	93.0	94.0	95.0
Lumiance (%)	63.5	63.5	63.5
Purity (%)	4.5	4.5	4.5
Dominant Wavelength (nm)	575	575	575

The values given are set values and variations occur.
Optical values measured by Elrepho 2000, calibrated
against master STFI Elrepho – (authorized by ISO)